

# Technical Data Sheet

Product name: PETG-CF

Version: 1.0

Date: 01.21.2024



MAERTZ

## Dimensions

Size	Ø tolerance	Roundness
1,75 mm	± 0.05 mm	± 0.05 mm
2,85 mm	± 0,10 mm	± 0,10 mm

## MATERIAL PROPERTIES

Description	Typical value	Test method
Density	1.1836g/cc	ISO 1183, GB/T 1033
Melt Index (MFR)	1.80 g/ min ( 190 °C/2,16kg )	ISO 1133, GB/T 3682
Glass Transition Temperature	65.3 °C	DSC, 10 °C/min
Melting Temperature	134.06 °C	DSC, 10 °C/min
Crystallization Temperature	99.35855%	DSC, 10 °C/min
Vicat Softening Temperature	67 °C	ISO306, GB/T1633
Heat Deflection Temperature	N/A	ISO 75 1.8MPa
Heat Deflection Temperature	N/A	ISO 75 0.45MPa
Tensile Strength at Yield	47.495 MPa	ISO 527, GB/T 1040
Strain at Yield	13.116%	ISO 527, GB/T 1040
Strain at Break	17.029%	ISO 527, GB/T 1040
E-Modulus	382.921MPa	ISO 527, GB/T 9341
Bending Modulus	2127.100MPa	ISO 178, GB/T 9341
Bending Strength	67.992MPa	ISO 178, GB/T 9341
Impact Strength	2.626 kJ/ m <sup>2</sup>	ISO 179, GB/T 1043
Layer Adhesion (Impact Strength - Z)	2.905 kJ/ m <sup>2</sup>	ISO 179, GB/T 1043
Moisture Absorption	0.09%	ISO 62 23°C , 50% RH

## GUIDELINE FOR PRINT SETTINGS

Description	Typical value
Printing Temperature	240 – 280 °C
Build Plate Compatibility	BuildTak®, Glass,BlueTape,PEI
Bed Temperature	70-100°C (Glue Recommended)
Cooling Fan	100%
Drying Settings	70-85°C (Blast Drying Oven)
Printing Speed	50-300(mm/s)
AMS Compatibility	YES
Raft Separation Distance	0.2(mm)Settings are based on a 0.4mm nozzle.
Retraction Speed	40(mm/s)
Hotend Compatibility	0.2mm,0.3mm,0.4mm,0.6mm,0.8mm 1.0mm nozzle.
Environmental Temperature	30°C Roomtemperature

### Packaging:

All spools are sealed and packed with silica gel to avoid humidity.

### Additional info:

The typical values presented in this data sheet are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly with printing conditions. End-use performance of printed parts depends not only on materials, but also on part design, environmental conditions, printing conditions, etc. Product specifications are subject to change without notice. Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/recycling practices of Maertz materials for the intended application. Maertz makes no warranty of any kind, unless announced separately, to the fitness for any use or application. Maertz shall not be made liable for any damage, injury, or loss induced from the use of Maertz materials in any application.

### Storage:

Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.