

Technical Data Sheet

Product Name: PLA Matte

Version: 1.0

Date: 21.01.2024



MAERTZ

Dimensions

Size	∅ tolerance	Roundness
1,75 mm	± 0.05 mm	± 0.05 mm
2,85 mm	± 0,10 mm	± 0,10 mm

Material Properties

Description	Typical value	Test method
Density	1.3412 g/cc	ISO 1183, GB/T 1033
Meltindex (MFR)	13.46g/10 (210 °C/2,16kg)	min ISO 1133, GB/T 3682
Glasstransition temperature	62.3°C	DSC,10°C/min
Melting temperature	152.51°C	DSC,10°C/min
Crystallinity		DSC,10°C/min
Vicat Softening Temperature	61.5°C	ISO306, GB/T1633
Heat Deflection Temperature	51.5°C	ISO 75 1.8MPa
Heat Deflection Temperature	55.7°C	ISO 75 0.45MPa
Tensile Strength at Yield	30.053 MPa	ISO 527, GB/T 1040
Strain at Yield	8.119%	ISO 527, GB/T 1040
Strain at Break	12.937%	ISO 527, GB/T 1040
E-Modulus	407.171 MPa	ISO 527, GB/T 9341
Bending Modulus	2546.901MPa	ISO 178, GB/T 9341
Bending Strength	52.427MPa	ISO 178, GB/T 9341
Impact Strength	3.246 kJ/ m ²	ISO 179, GB/T 1043
Layer Adhesion (Impact Strength - Z)	2.427 kJ/ m ²	ISO 179, GB/T 1043
Moisture absorption	0.09%	ISO 62 23°C, 50% RH

Technical Data Sheet

Guidelines for Print Settings

Description	Typical value
Printing Temperature	200 – 240 °C
Build Plate Compatibility	BuildTak®, Glass, BlueTape, PEI
Bed Temperature	55-70°C (Glue Recommended)
Cooling Fan	100%
Drying Settings	45-50°C (Blast Drying Oven)
Printing Speed	50-300(mm/s)
AMS Compatibility	YES
Raft Separation Distance	0.2(mm) Settings are based on a 0.4mm nozzle.
Retraction Speed	30(mm/s)
Hotend Compatibility	0.2mm, 0.3mm, 0.4mm, 0.6mm, 0.8mm 1.0mm nozzle.
Environmental Temperature	25°C Roomtemperature

Packaging:

All spools are sealed and packed with silica gel to prevent moisture.

Handling and Storage:

The typical values in this datasheet are provided for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly depending on printing conditions. The final performance of printed parts depends not only on the materials but also on design, environmental conditions, printing parameters, and other factors. Product specifications are subject to change without prior notice. Each user is responsible for determining the safety, legality, technical suitability, and disposal/recycling practices of Maertz materials for their intended application. Maertz provides no warranty unless specifically announced for suitability for a particular use or application. Maertz is not liable for any damages, injuries, or losses caused using Maertz materials in any application.

Storage:

Kühl und trocken (15-25°C) und fern von UV-Licht lagern. Dies verbessert die Haltbarkeit erheblich.